





INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07D 311/00	A2	(11) International Publication Number: WO 98/42693 (43) International Publication Date: 1 October 1998 (01.10.98)
(21) International Application Number: PCT/GB98/00904 (22) International Filing Date: 25 March 1998 (25.03.98) (30) Priority Data: 9706202.0 25 March 1997 (25.03.97) GB (71) Applicant (for all designated States except US): JAMES ROBINSON LIMITED [GB/GB]; Hillhouse Lane, P.O. Box 83, Huddersfield HD1 6BU (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): CLARKE, David, Allan [GB/GB]; 23 Wentworth Court, Rastrick, Brighouse HD6 3XD (GB). HERON, Bernard, Mark [GB/GB]; 63 Welton Road, Brough, East Riding, Yorkshire HU15 1AB (GB). GABBUTT, Christopher, David [GB/GB]; 7 New Row, Knowle Green, Preston, Lancashire PR3 2YS (GB). HEPWORTH, John, David [GB/GB]; 2 Carnoustie Close, Fulwood, Preston, Lancashire PR2 7ER (GB). PARTINGTON, Steven, Michael [GB/GB]; 48 Woodroyd, Golcar, Huddersfield HD7 4PG (GB). CORNS, Stephen, Nigel [GB/GB]; 10 Beech Street, Paddock, Huddersfield HD1 4JN (GB).		(74) Agents: WAIN, Christopher, Paul et al.; A.A. Thornton & Co., Northumberland House, 303-306 High Holborn, London WC1V 7LE (GB). (81) Designated States: GB, JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published Without international search report and to be republished upon receipt of that report.

(54) Title: NEUTRAL COLOURING PHOTOCHROMIC 2H-NAPHTHO[1,2-b]PYRANS AND HETEROCYCLIC PYRANS



(57) Abstract

A naphtho[1,2-*b*]pyran of general formula (I) wherein R¹ and R² are each selected from unsubstituted, mono-, di- or polysubstituted aryl groups, phenyl and naphthyl and heteroaryl groups. R⁵ is selected from linear or branched C₁-C₁₀ alkyl, C₁-C₂₀ cycloalkyl, C₁-C₂₀ bicycloalkyl, C₁-C₂₀ polycycloalkyl, linear or branched C₁-C₁₀ haloalkyl, linear or branched C₁-C₁₀ perhaloalkyl, linear or branched C₁-C₁₀ perhaloalkenyl, linear or branched C₁-C₁₀ alkenyl, C₁-C₁₀ alkynyl, linear or branched C₁-C₁₀ alkoxy, linear or branched C₁-C₁₀ alkylthio, linear or branched C₁-C₁₀ alkoxy (linear or branched C₁-C₁₀ alkyl), linear or branched C₁-C₁₀ hydroxyalkyl, linear or branched C₁-C₁₀ aminoalkyl, aryl, phenyl, heteroaryl, halogen, nitrile, nitro, amino, linear or branched C₁-C₂₀ alkoxy carbonyl, hydroxyl, formyl, acetyl, amido, C₁-C₅ alkyl amido, C₁-C₅ dialkylamido, aroyl, benzoyl, alkyl C₁-C₅ amino, dialkyl C₁-C₅ amino, arylamino, diarylamino, aryl C₁-C₅ alkylamino and cyclicamino groups, arylsulfinyl, arylsulfonyl, arylsulfonyl, linear or branched C₁-C₁₀ alkylsulfonyl, P(O)(O-C₁-C₁₀ alkyl)₂ or is an alkenyl function of general formula (a) wherein R¹¹ and/or R¹² and/or R¹³ is hydrogen or R⁵, R³, R⁴, R⁶, R⁸ and R¹⁰ are each hydrogen, R¹, R² or R⁵; and R⁷ and/or R⁹ is hydrogen or an amino group provided that R⁷ and R⁹ are not both hydrogen. The compounds may be combined with a polymeric host material such as plastic or glass to make a sunglass lens, an ophthalmic lens or a window.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		


- 1 -

Neutral Colouring Photochromic 2*H*-Naphtho[1,2-*b*]pyrans and Heterocyclic Pyrans

The present invention relates to certain new photochromic pyran derivatives and to their use.

Photochromism is a well-known physical phenomenon which is observed with certain classes of chemical compounds. A detailed discussion of this phenomenon can be found in "Photochromism: Molecules and Systems," Studies in Organic Chemistry 40, Eds. H Dürr and H. Bouas-Laurent, Elsevier, 1990.

The 2*H*-naphtho[1,2-*b*]pyran system is known to be capable of exerting a photochromic effect as described, for example, U. S. Patent No. 3,567,605 and U. S. Patent No. 4,826,977. U. S. Patent No. 3,567,605 provides an example of a 2*H*-naphtho[1,2-*b*]pyran which remains coloured at ambient temperatures for several hours, and U. S. Patent No. 4,826,977 describes a series of yellow/orange colouring 2*H*-naphtho[1,2-*b*]pyrans containing a spiro-adamantane group at the 2-position, amongst other 2*H*-[1]benzopyran and isomeric naphthopyran systems. The basic structural unit of the 2*H*-naphtho[1,2-*b*]pyran system, in this instance substituted at C-2 with a spiro-adamantane group, is illustrated below.



A range of purple/blue colouring 2(4-aminophenyl)-2-alkyl-2*H*-naphtho[1,2-*b*]pyrans have also been described in U. S. Patent No. 4,818,096.

A series of photochromic 2*H*-naphtho[1,2-*b*]pyrans, amongst other 2*H*-[1]benzopyrans and isomeric naphthopyrans, bearing a cyclopropyl group as one of the substituents at the 2-position is described in article WO92/01959. It is also commented that the compound 2-cyclopropyl-2-*p*-methoxyphenyl-5-methyl-2*H*-naphtho[1,2-*b*]pyran and several other analogues are of particular current interest, but no reasons were presented either to substantiate such interest or on any significance of the 5-methyl group.

- 2 -

It is stated in U. S. Patent No. 5,066,818 (1991) that "The compound, 2,2-diphenyl-2*H*-naphtho[1,2-*b*]pyran, also colours on exposure to near ultraviolet light at room temperature but does not bleach in a reasonable period of time. Substitution of the phenyl substituents in the *meta* and *para* positions have little effect on the rate of bleaching of these compounds."

The very high optical density of 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyrans achieved under irradiation and their slow attendant fade (bleaching) on removal of the source of irradiation relative to the photochromic properties displayed by the isomeric 3,3-diaryl-3*H*-naphtho[2,1-*b*]pyrans has been recently noted by B. van Gemert *et al.* (*Mol. Cryst. Liq. Cryst.*, 1994, 246, 67). The relatively slow attendant fade of the 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyrans was rationalised by the absence of steric crowding in the ring opened (coloured) quinoidal/zwitterionic forms. Such steric crowding is thought to be present for the ring opened form of the 3,3-diaryl-3*H*-naphtho[2,1-*b*]pyrans and accounts for their relatively rapid fade.


Pilkington Brothers Limited have also commented on the fading of photochromic materials in Research Disclosure. Two structurally similar deep colouring photochromic 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyrans, namely 2,2-bis(4-methoxyphenyl)-5,6-dimethyl-2*H*-naphtho[1,2-*b*]pyran and 2-(4-methoxyphenyl)-2-(4-trifluoromethylphenyl)-5,6-dimethyl-2*H*-naphtho[1,2-*b*]pyran are described, which exhibit markedly improved attendant fade compared with the non-methyl substituted analogues. These improved rates of fade are attributed to the combined presence of methyl groups at the 5- and 6-positions, which are said to exert steric pressures upon the ring opened (coloured) quinoidal/zwitterionic forms, thereby enhancing the ring closure to the uncoloured naphthopyran system. However, these fast fade materials described by Pilkington plc with substituents at both the 5- and 6- positions are difficult to make, requiring a long multi-stage process which renders them unattractive commercially. Thus the use of two substituents at the 5- and 6-positions to achieve rapid fade in these 2,2-diaryl compounds has the disadvantage of manufacture complexities.

Two recent U. S. Patents, 5,458,814 and 5,514,817 describe the synthesis of a range fast fading intense yellow to red/purple colouring 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyrans and phenanthropyran which either possess a 5-substituent or are 5,6-disubstituted.

- 3 -

We have investigated these known photochromic compounds and have found that, for intense colour generation, compounds having 2,2-diaryl substituents are preferred. Also the presence of a 5 substituent in these 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyrans ensures rapid fading of the colour generated upon irradiation. Furthermore, we have found that brown and brown/red photochromic 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyrans can be obtained when the said, 2,2-diaryl-2*H*-naphtho[1,2-*b*]pyran is substituted in the 7- or 9-position with an amino function.

According to the present invention, there is provided a photochromic compound of the formula I



I

In graphic formula I above, R¹ and R² are each selected from unsubstituted, mono-, di- or polysubstituted aryl groups, phenyl and naphthyl, preferably mono- or di-substituted phenyl or naphthyl. Additionally R¹ and or R² may be selected from the following heteroaryl groups, thienyl, benzo[*b*]thienyl, furyl, benzo[*b*]furyl, pyrrolyl, indolyl, pyridyl, quinolyl, isoquinolyl, pyrimidyl, oxazolyl, isoxazolyl, thiazolyl, isothiazolyl, pyrazolyl, imidazolyl, benzimidazolyl.

The substituents for the aryl and heteroaryl groups representing R¹ and R² may be C₁ - C₅ alkyl, C₁ - C₅ haloalkyl, C₁ - C₅ alkoxy, C₁ - C₅ alkoxy(C₁ - C₅)alkyl, amino-C₁ - C₅ alkyl, hydroxy-C₁ - C₅ alkyl, halogen, amino, alkyl C₁ - C₅ amino, dialkyl C₁ - C₅ amino and cyclic amino groups (for example, aziridino, pyrrolidino, piperidino, morpholino, thiomorpholino, indolino, piperazino, C₁ - C₅ N-alkylpiperazino).

Phenyl, aryl and heteroaryl ring substituents may be located at the *o*-, *m*- or *p*-positions. Typically, each phenyl group contains less than 3 substituents.


R³ and R⁴ are hydrogen

R⁵ may be selected from C₁ - C₁₀ alkyl, C₁ - C₁₀ haloalkyl, C₁ - C₁₀ perfluoroalkyl, C₁ - C₅ perfluoroalkenyl, C₁ - C₅ alkenyl, C₁ - C₅ alkynyl, C₁ -

- 4 -

C₁₀ alkoxy, C₁ - C₁₀ perfluoroalkoxy, C₁ - C₅ alkoxy(C₁ - C₅) alkyl, C₁ - C₅ hydroxyalkyl, halogen, nitrile, nitro, amino, C₁ - C₅ alkylamino, C₁ - C₅ dialkylamino, cyclic amino (for example, aziridino, pyrrolidino, piperidino, morpholino, thiomorpholino, indolino, piperazino, C₁ - C₅ N-alkyl-piperazino), arylamino, diarylamino, aryl C₁ - C₅ alkylamino, C₁ - C₅ oxoalkyl, phenyl, aryl, substituted aryl, naphthyl, substituted naphthyl, aroyl, substituted aroyl, formyl, carboxyl, C₁ - C₂₀ alkoxycarbonyl, C₁ - C₅ haloalkyloxycarbonyl, aryloxycarbonyl, substituted aryloxycarbonyl.

R⁵ may also be selected from the alkenyl function illustrated immediately below:



Where R¹¹ and or R¹² and or R¹³ will be selected from those substituents specified above for R⁵ in formula I. In addition to these substituents R¹¹ and R¹² and R¹³ may be selected from H, CN, NO₂, CHO, C₁ - C₅ alkoxycarbonyl, benzoyl, and phenylsulfonyl.



In graphic formula I R⁶ and R⁸ and R¹⁰ may be selected from hydrogen, in addition to those groups specified for R⁵ above.

To impart a brown or brown/red colour in the darkened state R⁹ and or R⁷ are selected from amino, substituted amino including alkyl C₁ - C₅ amino, dialkyl C₁ - C₅ amino, arylamino, aryl alkyl C₁ - C₅ amino, diarylamino and cyclic amino groups (for example, aziridino, pyrrolidino, piperidino, morpholino, thiomorpholino, indolino, piperazino, C₁ - C₅ N-alkylpiperazino), this selection is illustrative and not limiting.

Typically, though not always, two or three groups selected from R⁷, R⁸, R⁹ and R¹⁰ are hydrogen though at least one of R⁷ and R⁹ will be an amino function.



In addition to the 2*H*-naphtho[1,2-*b*]pyran compounds of formula I, the present invention includes the isomeric phenanthropyrans of the general formula II and III

- 5 -



In graphic formula II and III R^1 to R^{13} are as specified for graphic formula I and R^{14} may be selected from those substituents specified for R^6 .

In addition to the 2H-naphtho[1,2-b]pyran compounds of formula I, the present invention includes the isomeric heterocyclic pyrans of the general formula IV and V. These compounds are extremely rapid fading brown or brown/red photochromic compounds. The presence of a function other than hydrogen at R^5 is again essential for the extremely rapid bleaching of the coloured state, with the heteroatom responsible for the brown or brown/red colouration.



In graphic formula IV and V R^1 to R^{14} are as specified for graphic formula I and the heteroatom X may be selected from O, S, NH, and substituted N for example $C_1 - C_{10}$ alkyl, $C_1 - C_{10}$ haloalkyl, $C_1 - C_{10}$ perfluoroalkyl, benzyl, phenyl, tosyl, benzoyl, amino- $C_1 - C_5$ alkyl, hydroxy- $C_1 - C_5$ alkyl.

The photochromic properties exhibited by the novel pyran compounds of the present invention, namely those of high induced optical density and rapid bleaching of the brown, red/brown coloured form, render these compounds particularly useful as photochromic materials for incorporation into polymeric host materials so as to impart photochromic properties to the said polymeric host materials. Examples of applications of the polymeric host materials containing photochromic materials of the present invention include

-6-


The manufacture of lenses for sunglasses and ophthalmic lenses, optical filters and windows for vehicles such as cars (including sunroofs), aircraft and ships and architectural uses e.g. windows for homes and for photochromic 'stained glass' windows.

The photochromic pyrans of the present invention are incorporated into the 'plastic' host material by well established protocols for example as described in European patent no. 0254020 or U.S. patent no. 5,066,818.

The high induced optical density of the photochromic compounds of the present invention enables the amount of the photochromic material required so as to impart a useful degree of photochromism to a polymeric host material or to a solution to be greatly reduced, thereby enabling a considerable saving of synthetic effort and cost. Furthermore, the use of reduced quantities of the photochromic materials of the present invention has the bonus that there is a consequent reduction in any undesirable colour that the photochromic materials may impart in the bleached state, either by way of inherent colour of the material itself or by the formation of coloured fatigue/degradation products through use of the photochromic material.

Typical host materials are optically clear polymer materials, such as polymers of polyol (allyl carbonate) - monomers, polyacrylates such as polymethylmethacrylates, cellulose acetate, cellulose triacetate, cellulose acetate propionate, cellulose acetate butyrate, poly(vinyl acetate), poly(vinyl alcohol), polyurethanes, polycarbonate, polyethylene terephthalate, polystyrene, poly(triethyleneglycol dimethylacrylate), poly(diethyleneglycol bis(allyl carbonate)) and various copolymer mixes.

The pyran compounds of the present invention may be prepared by a general method which is based on the following reaction scheme:



- 7 -

This general synthetic methodology has been described in detail, for example, by L. Merlini in 'Advances in Heterocyclic Chemistry,' 1975, vol. 18, page 159, and by R. Guglielmetti in "Photochromism: Molecules and Systems," Studies in Organic Chemistry 40, chp. 8, Eds. H Dürr and H. Bouas-Laurent, Elsevier, 1990, and also in several patent documents, for example, U. S. Patent No. 5,066,818; U. S. Patent No. 4,990,287, WO 92/09593 and WO95/05382. The synthesis of the propargyl alcohols shown in the scheme above are obtained in a known manner, for example, T. F. Rutledge in 'Acetylenic Compounds,' Reinhold, New York, 1968. The 1-naphthols and related hydroxy compounds are either commercially available or obtained by known synthetic methods, or derived from such methods. Some of the 1-naphthols and related hydroxy compounds or precursors thereof have been described in the chemical literature, for example, ethyl 1-acetoxydibenzo thiophene-3-carboxylate see (S. Gronowitz *et al.*, Acta. Pharm. Suec., 1978, 15, 337) and 3-hydroxypropyl-1-naphthol see (R. F. Frank *et al.*, J. Chem. Soc., Chem. Commun., 1984, 761). The use of the Stobbe condensation to prepare 1-naphthols has also been discussed (see Organic Reactions 1951, 6, 1). The acid catalyst may be selected from acidic alumina (Brockmann 1), acetic acid, trifluoroacetic acid, silica, clays (e.g. montmorillonite, tonsil) or acidic exchange resins. Organic solvents frequently employed for the reaction include benzene, toluene, xylene and relatively high boiling alkanes.

- 8 -

The following examples illustrate but do not limit the invention:

Example 1: Methyl 2,2-bis(4-methoxyphenyl)-9-morpholino-2*H*-naphtho [1,2-*b*]pyran-5-carboxylate


(a) Ethyl 4-acetoxy-6-morpholino-2-naphthoate.

A solution of 4-morpholinobenzaldehyde (11g, 57.5 mmol) and diethyl succinate (15.03g, 86.3 mmol) in anhydrous ethanol (50 cm³) was added dropwise over 45 minutes to a vigorously stirred warm ~ 40 - 50 °C, solution of sodium ethoxide (from sodium 2.64g, 115 mmol) in anhydrous ethanol (250 cm³) under N₂. On completion of the addition the solution was refluxed for 4 hours and then cooled to room temperature.

The reaction mixture was reduced to ~ 1/5 of the original volume and the resulting viscous oil was diluted with water (500 cm³), cautiously neutralised with HCl (2M) and the resulting two phase mixture extracted with ethyl acetate (5 x 50 cm³). The combined EtOAc solutions were extracted with aq. sat. NaHCO₃ solution (5 x 75 cm³). The combined aq. NaHCO₃ solutions were cautiously neutralised with HCl (2M) and the resulting two phase mixture extracted with EtOAc (4 x 75 cm³). The combined EtOAc extracts were dried (Na₂SO₄) and evaporated to afford a red/brown solid.

A solution of the foregoing red/brown solid and anhydrous sodium acetate (4.72g, 57.5 mmol) in acetic anhydride (100 cm³) was refluxed for 3 hours. The solution was cooled to room temperature and then diluted with water (1200 cm³) and allowed to stir for 1.5 hours. The resulting pale brown solid was collected by vacuum filtration, washed well with water (~300 cm³) and air dried.


The solid was recrystallised from EtOAc / hexane and Norit (activated charcoal) to give ethyl 4-acetoxy-6-morpholino-2-naphthoate (yield = 14.6 g, theoretical yield = 19.75 g, 73.9 %, m. p. = 135 - 137 °C (uncorrected)).



(b) Methyl 4-hydroxy-6-morpholino-2-naphthoate.

- 9 -


A solution of ethyl 4-acetoxy-6-morpholino-2-naphthoate (12.0g, 34.9 mmol) and sodium hydroxide (8.4g, 210 mmol) in water (200 cm³) and ethanol (40 cm³) was maintained at 80 - 90 °C for 3 hours. The cooled solution was poured into water (750 cm³) and cautiously neutralised with HCl (2M). The resulting suspension was extracted with EtOAc (5 x 100 cm³). The combined extracts were dried (Na₂SO₄) and evaporated to give a brown solid. This solid was dissolved in methanol (200 cm³) containing c. H₂SO₄ (~ 3 cm³) and was refluxed for 5 hours. The cooled mixture was diluted with water (900 cm³) and aq. sat. NaHCO₃ solution (100 cm³) then extracted with EtOAc (6 x 50 cm³). The combined extracts were washed with aq. sat. NaHCO₃ (4 x 100 cm³) and water (100 cm³). Removal of the dried (Na₂SO₄) EtOAc gave a pale brown solid which was recrystallised from EtOAc/hexane to afford methyl 4-hydroxy-6-morpholino-2-naphthoate (yield = 5.14g, theoretical yield = 10.0g, 51.2%, m.p. = 231 - 233.5 °C (uncorrected)).




(c) Methyl 2,2-bis(4-methoxyphenyl)-9-morpholino-2H-naphtho[1,2-b]pyran-5-carboxylate.

A solution of methyl 4-hydroxy-6-morpholino-2-naphthoate (1.0g, 3.5 mmol) and 1,1-di(4-methoxyphenyl)prop-2-yn-1-ol (0.94g, 3.5 mmol) in toluene (45 cm³) containing acidic alumina (Brockmann 1), (5.0g) was refluxed for 100 minutes. The cooled solution was filtered and the alumina was washed well with EtOAc (200 cm³). The organic filtrate was washed with aqueous sodium hydroxide (2M, 2 x 50 cm³) and water (100 cm³). Removal of the dried (Na₂SO₄) EtOAc gave an oil which was flash chromatographed over silica using 35% EtOAc in hexane as the eluent to afford a pale yellow solid. Recrystallisation from EtOAc/hexane gave methyl 2,2-bis(4-methoxyphenyl)-9-morpholino-2H-naphtho[1,2-b]pyran-5-carboxylate (yield = 0.28g, theoretical yield = 1.87g 15%, m.p. = 153.5 - 155 °C (uncorrected)).


- 10 -



Example 2: Methyl 2,2-bis(4-methoxyphenyl)-9-pyrrolidino-2H-naphtho[1,2-b]pyran-5-carboxylate, m.p. = 193 - 194 °C (uncorrected). This compound was obtained by a similar protocol to example 1 above starting from 4-pyrrolidinobenzaldehyde.



Example 3: Methyl 2,2-bis(4-methoxyphenyl)-9-dimethylamino-2H-naphtho[1,2-b]pyran-5-carboxylate, m.p. = 168 - 169 °C (uncorrected). This compound was obtained by a similar protocol to example 1 above starting from 4-dimethylamino-benzaldehyde.



Example 4: Methyl 11,11-di(4-methoxyphenyl)-2-methyl-11H-pyrano[2,3-b]carbazole-8-carboxylate.

(a) Ethyl 1-acetoxy-9-methylcarbazole-3-carboxylate.


- 11 -

A solution of 1-methylindole-3-carboxaldehyde (10.17g, 63.9 mmol) and diethyl succinate (11.7g, 67.1 mmol) in anhydrous ethanol (50 cm³) was added dropwise over 45 minutes to a vigorously stirred warm ~ 40 - 50 °C, solution of sodium ethoxide (from sodium 2.93g, 128 mmol) in anhydrous ethanol (300 cm³) under N₂. On completion of the addition the solution was refluxed for 48 hours and then left to stand at RT for 64 hours.

The reaction mixture was reduced to ~ 1/5 of the original volume and the resulting viscous oil was diluted with water (700 cm³), cautiously acidified with c. HCl and the resulting two phase mixture extracted with ethyl acetate (5 x 100 cm³). The combined EtOAc extracts were washed with water (100 cm³), dried (Na₂SO₄) and evaporated to afford a sticky orange solid.

A solution of the foregoing solid and anhydrous sodium acetate (5.24g, 63.9 mmol) in acetic anhydride (90 cm³) was refluxed for 3 hours. The solution was cooled to room temperature and then diluted with water (1500 cm³) and allowed to stir for 1.5 hours. The resulting pale brown solid was collected by vacuum filtration, washed well with water (~500 cm³) and air dried.

The solid was recrystallised from EtOAc / hexane and Norit (activated charcoal) to give ethyl 1-acetoxy-9-methylcarbazole-3-carboxylate (yield = 6.2 g, theoretical yield = 19.9 g, 32.6 %, m. p. = 123 -125 °C (uncorrected)).




(b) Methyl 1-hydroxy-9-methylcarbazole-3-carboxylate.

A solution of ethyl 1-acetoxy-9-methylcarbazole-3-carboxylate (5.43g, 17 mmol) and sodium hydroxide (3.48g, 87 mmol) in water (150 cm³) and ethanol (40 cm³) was maintained at 80 - 90 °C for 3 hours. The cooled solution was poured into water (400 cm³) and cautiously acidified with c. HCl. The resulting suspension was extracted with EtOAc (5 x 75 cm³). The combined extracts were dried (Na₂SO₄) and evaporated to give an orange/brown solid. This solid was dissolved in methanol (100 cm³) containing c. H₂SO₄ (~ 1 cm³) and was refluxed for 4 hours. The cooled mixture was diluted with water (500 cm³) and extracted with EtOAc (4 x 50 cm³). The


- 12 -

combined extracts were washed with aq. sat. NaHCO_3 ($2 \times 100 \text{ cm}^3$) and water (100 cm^3). Removal of the dried (Na_2SO_4) EtOAc gave an orange brown solid which was recrystallised from EtOAc/hexane to afford methyl 1-hydroxy-9-methylcarbazole-3-carboxylate (yield = 3.37g, theoretical yield = 4.45g, 75.7%, m.p. = $204 - 206.5^\circ\text{C}$ (uncorrected)).



(c) Methyl 11,11-di(4-methoxyphenyl)-2-methyl-11H-pyrano[2,3-b]carbazole-8-carboxylate.

A solution of methyl 1-hydroxy-9-methylcarbazole-3-carboxylate (1.0g, 3.9 mmol) and 1,1-di(4-methoxyphenyl)prop-2-yn-1-ol (1.05g, 3.9 mmol) in toluene (45 cm^3) containing acidic alumina (Brockmann 1), (4.0g) was refluxed for 35 minutes. The cooled solution was filtered and the alumina was washed well with EtOAc (200 cm^3). The organic filtrate was washed with aqueous sodium hydroxide (2M, $2 \times 50 \text{ cm}^3$) and water (100 cm^3). Removal of the dried (Na_2SO_4) EtOAc gave an oil which was flash chromatographed over silica using 25% EtOAc in hexane as the eluent to afford a pale orange solid. Recrystallisation from EtOAc/hexane gave methyl 11,11-di(4-methoxyphenyl)-2-methyl-11H-pyrano[2,3-b]carbazole-8-carboxylate (yield = 1.10g, theoretical yield = 1.98g 55.5%, m.p. = $185.5 - 188.0^\circ\text{C}$ (uncorrected)).




Example 5: Methyl 2,2-di(4-methoxyphenyl)-2H-benzo[b]thieno[2,3-h][1]benzopyran-5-carboxylate.

(a) Methyl 1-hydroxydibenzothiophene-3-carboxylate.

- 13 -


A solution of ethyl 1-acetoxydibenzothiophene-3-carboxylate (12.8g, 40.7 mmol) and sodium hydroxide (8.14g, 203.6 mmol) in water (200 cm³) and ethanol (50 cm³) was maintained at 80 - 90 °C for 3 hours. The cooled solution was poured into water (600 cm³) and cautiously acidified with c. HCl. The resulting suspension was extracted with EtOAc (5 x 75 cm³). The combined extracts were dried (Na₂SO₄) and evaporated to give a brown solid. This solid was dissolved in methanol (150 cm³) containing c. H₂SO₄ (~ 1.5 cm³) and was refluxed for 6 hours. The cooled mixture was diluted with water (700 cm³) and extracted with EtOAc (5 x 50 cm³). The combined extracts were washed with aq. sat. NaHCO₃ (3 x 100 cm³) and water (100 cm³). Removal of the dried (Na₂SO₄) EtOAc gave a dark brown solid which was recrystallised from EtOAc/hexane to afford methyl 1-hydroxy-dibenzothiophene-3-carboxylate (yield = 6.07g, theoretical yield = 10.51g, 58%, m.p. = 231.5 - 234 °C (uncorrected)).



(b) Methyl 2,2-di(4-methoxyphenyl)-2H-benzo[b]thieno[2,3-h][1]benzo-pyran-5-carboxylate.

A solution of methyl 1-hydroxy-dibenzothiophene-3-carboxylate (1.0g, 3.87 mmol) and 1,1-di(4-methoxyphenyl)prop-2-yn-1-ol (1.04g, 3.87 mmol) in toluene (45 cm³) containing acidic alumina (Brockmann 1), (4.0g) was refluxed for 20 minutes. The cooled solution was filtered and the alumina was washed well with EtOAc (200 cm³). The organic filtrate was washed with aqueous sodium hydroxide (2M, 2 x 50 cm³) and water (100 cm³). Removal of the dried (Na₂SO₄) EtOAc gave a red orange solid. Recrystallisation from PhMe/EtOAc/hexane gave methyl 2,2-di(4-methoxyphenyl)-2H-benzo[b]thieno[2,3-h][1]benzo-pyran-5-carboxylate (yield = 1.01g, theoretical yield = 1.97g 51.2%, m.p. = 205.5 - 207 °C (uncorrected)).

- 14 -



Comparative example 1: Methyl 9-methoxy-2,2-bis(4-methoxyphenyl)-2H-naphtho[1,2-b]pyran-5-carboxylate


(a) Ethyl 4-acetoxy-6-methoxy-2-naphthoate

A solution of freshly distilled *p*-anisaldehyde (20g, 146.9 mmol) and diethyl succinate (38.4g, 220.3 mmol) in anhydrous ethanol (50 cm³) was added dropwise over 45 minutes to a vigorously stirred warm ~ 40 - 50 °C, solution of sodium ethoxide (from sodium 6.75g, 293.8 mmol) in anhydrous ethanol (450 cm³) under N₂. On completion of the addition the solution was refluxed for 4 hours and then cooled to room temperature.

The reaction mixture was reduced to ~ 1/5 of the original volume and the resulting viscous oil was diluted with water (700 cm³), cautiously acidified with c. HCl and the resulting two phase mixture extracted with ethyl acetate (5 x 100 cm³). The combined EtOAc solutions were extracted with aq. sat. NaHCO₃ solution (6 x 100 cm³). The combined aq. NaHCO₃ solutions were cautiously acidified with c. HCl and the resulting two phase mixture extracted with EtOAc (4 x 100 cm³). The combined EtOAc extracts were dried (Na₂SO₄) and evaporated to afford a yellow mobile oil.


A solution of the foregoing yellow oil and anhydrous sodium acetate (12.05g, 146.9 mmol) in acetic anhydride (180 cm³) was refluxed for 3 hours. The solution was cooled to room temperature and then diluted with water (2000 cm³) and allowed to stir for 1.5 hours. The resulting pale brown solid was collected by vacuum filtration, washed well with water (~500 cm³) and air dried.

The solid was recrystallised from EtOAc / hexane and Norit (activated charcoal) to give ethyl 4-acetoxy-6-methoxy-2-naphthoate (yield = 21.2 g, theoretical yield = 42.35 g, 50 %, m. p. = 103.5 -104.5 °C (uncorrected)).



(b) Methyl 4-hydroxy-6-methoxy-2-naphthoate

A solution of ethyl 4-acetoxy-6-methoxy-2-naphthoate (3.0g, 10.4 mmol) and sodium hydroxide (2.5g, 62.5 mmol) in water (60 cm³) and ethanol (15 cm³) was maintained at 80 - 90 °C for 3 hours. The cooled solution was poured into water (400 cm³) and cautiously acidified with c. HCl. The resulting suspension was extracted with EtOAc (5 x 75 cm³). The combined extracts were dried (Na₂SO₄) and evaporated to give a pale brown solid. This solid was dissolved in methanol (50 cm³) containing c. H₂SO₄ (~ 1 cm³) and was refluxed for 4 hours. The cooled mixture was diluted with water (500 cm³) and extracted with EtOAc (4 x 50 cm³). The combined extracts were washed with aq. sat. NaHCO₃ (2 x 100 cm³) and water (100 cm³). Removal of the dried (Na₂SO₄) EtOAc gave a pale brown solid which was recrystallised from EtOAc/hexane to afford methyl 4-hydroxy-6-methoxy-2-naphthoate (yield = 1.63g, theoretical yield = 2.41g, 68%, m.p. = 193 - 195 °C (uncorrected)).




(c) Methyl 9-methoxy-2,2-bis(4-methoxyphenyl)-2H-naphtho [1,2-b]pyran-5-carboxylate.

A solution of methyl 4-hydroxy-6-methoxy-2-naphthoate (1.0g, 4.3 mmol) and 1,1-di(4-methoxyphenyl)prop-2-yn-1-ol (1.16g, 4.3 mmol) in toluene (45 cm³) containing acidic alumina (Brockmann 1), (4.0g) was refluxed for 45 minutes. The cooled solution was filtered and the alumina was washed well with EtOAc (200 cm³). The organic filtrate was washed with aqueous sodium hydroxide (2M, 2 x 50 cm³) and water (100 cm³). Removal of the dried (Na₂SO₄) EtOAc gave an oil which was flash chromatographed over silica using 25% EtOAc in hexane as the eluent to afford a pale yellow solid. Recrystallisation from EtOAc/hexane gave methyl

-16-


9-methoxy-2,2-bis(4-methoxyphenyl)-2*H*-naphtho[1,2-*b*]pyran-5-carboxylate (yield = 0.79g, theoretical yield = 2.08g 38%, m.p. = 162.5 - 164.0°C (uncorrected)).



-17-


CLAIMS:

1. A naphtho[1,2-*b*]pyran of general formula (I)



wherein R^1 and R^2 are each selected from unsubstituted, mono-, di- or polysubstituted aryl groups, phenyl and naphthyl and heteroaryl groups.

R^3 is selected from linear or branched C_1 - C_{10} alkyl, C_1 - C_{20} cycloalkyl, C_1 - C_{20} bicycloalkyl, C_1 - C_{20} polycycloalkyl, linear or branched C_1 - C_{10} haloalkyl, linear or branched C_1 - C_{10} perhaloalkyl, linear or branched C_1 - C_{10} perhaloalkenyl, linear or branched C_1 - C_{10} alkenyl, C_1 - C_{10} alkynyl, linear or branched C_1 - C_{10} alkoxy, linear or branched C_1 - C_{10} alkylthio, linear or branched C_1 - C_{10} alkoxy (linear or branched C_1 - C_{10} alkyl), linear or branched C_1 - C_{10} hydroxyalkyl, linear or branched C_1 - C_{10} aminoalkyl, aryl, phenyl, heteroaryl, halogen, nitrile, nitro, amino, linear or branched C_1 - C_{20} alkoxy carbonyl, hydroxyl, formyl, acetyl, amido, C_1 - C_3 alkyl amido, C_1 - C_3 dialkylamido, aroyl, benzoyl, alkyl C_1 - C_3 amino, dialkyl C_1 - C_3 amino, arylamino, diarylamino, aryl C_1 - C_3 alkylamino and cyclicamino groups, arylsulfinyl, arylsulfanyl, arylsulfonyl, linear or branched C_1 - C_{10} alkylsulfonyl, $P(O)(O-C_1-C_{10} \text{ alkyl})_2$ or is an alkenyl function of general formula:



-18-

wherein R¹¹ and/or R¹² and/or R¹³ is hydrogen or R⁵;

R³, R⁴, R⁶, R⁸ and R¹⁰ are each hydrogen, R¹, R² or R⁵; and

R⁷ and/or R⁹ is hydrogen or an amino group provided that R⁷ and R⁹ are not both hydrogen.



2. A naphtho[1,2-*b*]pyran according to claim 1, wherein the amino group of R⁷ and/or R⁹ is selected from amino, linear or branched alkyl C₁-C₁₀ amino, linear or branched dialkyl C₁-C₁₀ amino, arylamino, diarylamino, aryl, linear or branched C₁-C₁₀ alkylamino and cyclicamino groups.
3. A naphtho[1,2-*b*]pyran according to claim 1 or 2, wherein the heteroaryl group of R¹ and R² is thienyl, benzo[*b*]thienyl, furyl, benzo[*b*]furyl, pyrrol, indolyl, pyridyl, quinolyl, isoquinolyl, pyrimidyl, oxazolyl, isoxazolyl, thiazolyl, isothiazolyl, pyrazolyl, imidazolyl, benzimidazolyl, triazolyl, benzotriazolyl or tetrazolyl.
4. A naphtho[1,2-*b*]pyran according to claim 1, 2 or 3, wherein the substituents for the aryl, naphthyl and heteroaryl groups representing R¹ and R² are linear or branched C₁-C₂₀ alkyl, C₁-C₂₀ cycloalkyl, C₁-C₂₀ bicycloalkyl, C₁-C₂₀ polycycloalkyl, linear or branched C₁-C₁₀ haloalkyl, linear or branched C₁-C₁₀ perhaloalkyl, linear or branched C₁-C₁₀ perhaloalkenyl, linear or branched C₁-C₁₀ alkenyl, C₁-C₁₀ alkynyl, linear or branched C₁-C₁₀ alkoxy, linear or branched C₁-C₁₀ alkylthio, linear or branched C₁-C₁₀ alkoxy (linear or branched C₁-C₁₀ alkyl), linear or branched C₁-C₁₀ hydroxyalkyl, linear or branched C₁-C₁₀ aminoalkyl, aryl, phenyl, heteroaryl, halogen, nitrile, nitro, amino, linear or branched C₁-C₂₀ alkoxycarbonyl, hydroxyl, formyl, acetyl, amido, C₁-C₃ alkyl amido, C₁-C₃ dialkylamido, aroyl, benzoyl, alkyl C₁-C₃ amino, dialkyl C₁-C₃ amino, arylamino, diarylamino, aryl C₁-C₃ alkylamino and cyclicamino groups arylsulfinyl, arylsulfanyl,

- 19 -

arylsulfonyl, linear or branched C_1 - C_{10} alkylsulfonyl, $P(O)(O-C_1-C_{10} \text{ alkyl})_2$

5. A naphtho[1,2-*b*]pyran according to any preceding claim, wherein the cyclicamino group is aziridino, pyrrolidino, piperidino, morpholino, thiomorpholino, indolino, piperazino, C_1 - C_3 *N*-Alkylpiperazino or *N*-aryl piperazino.

6. A naphtho[1,2-*b*]pyran of the general formula II or III, according to any preceding claim,





wherein R^{14} is as defined for R^3 , R^4 , R^6 , R^8 and R^{10}

7. A naphtho[1,2-*b*]pyran according to claim 1, wherein R^1 and R^2 are each 4-methoxyphenyl, R^5 is methoxycarbonyl, and R^9 is morpholino, pyrrolidino or dimethylamino.

- 20 -

8. A naphtho[1,2-*b*]pyran of general formula IV or V according to claim 6



wherein X is selected from O, S, SO, SO₂, Se, NH, N-linear or branched C₁-C₁₀ alkyl, N-aryl, N-heteroaryl, N-linear or branched C₁-C₁₀ haloalkyl, N-linear or branched C₁-C₁₀ perhaloalkyl, N-linear or branched C₁-C₁₀ hydroxyalkyl, N-linear or branched C₁-C₁₀ alkoxyalkyl, benzyl, substituted benzyl, tosyl.

9. A naphtho[1,2-*b*]pyran according to claim 8, wherein X is NMe or S, R¹ and R² are each 4-methoxyphenyl and R⁵ is methoxycarbonyl.
10. A polymeric host material including a naphtho[1,2-*b*]pyran according to any preceding claim.
11. A polymeric host material according to claim 10, wherein the material is a plastic or a glass.
12. A window, an optical filter, an ophthalmic lens or a sunglass lens made from a polymeric host material according to claim 10 or 11.